



Carbon & Graphite Solutions



Typical Properties of Molded Graphite: "G" Series

Grade	Density	Electrical Resistivity	Coefficient of Thermal Expansion	Thermal Conductivity	Shore Hardness	Flexural Strength	Standard Sizes
	g/cm ³	μohm-m	x 10 ⁻⁶ /°C	Kcal/m-hr-°C	Shore	Mpa (=N/mm ²)	(in)
G140	1.7	8.5	3.8	125	25	15.7	24 X 46 X 72 Ø 39 * 39 Ø 32 * 39

* Non-Standard sizes may also be available upon request. Please check with your salesperson.

* Post Purification to < 5ppm and / or chemical coating on machined components is available.



1-800-966-4694

www.mwi-inc.com

We do not warrant the accuracy or applicability of the information contained herein or the suitability of the products described herein for any particular purpose.

© Copyright 2014 MWI Inc.